

	<b>CORE DIMENSIONS</b>					
	UNCOATED CORE			33T0231-000		
		MM	INCHES		MM	INCHES
OD	5.84	(.230)	±	.15	(.006)	
ID	3.05	(.120)	±	.13	(.005)	
TH	1.52	(.060)	±	.13	(.005)	
SINGLE PARYLENE COATING			33T0231-00P			
OD	5.87	(.231)	±	.15	(.006)	
ID	3.02	(.119)	±	.13	(.005)	
TH	1.55	(.061)	±	.13	(.005)	
INITIAL PERMEABILITY			2700			
WEIGHT / K			0.32 LBS			
ELECTRICAL SPECIFICATION						
	MIN	MIN TOL.	NOM	MAX	FREQ.	VOLT.
	(μH)		(μH)	(μH)	(kHz)	(V)
L	.428	(-20%)	.535	.642	100	≤ .00046
Q	62	-	-	-	100	≤ .00046
	TURN					
COATING SPECIFICATIONS						
	TYPE	coating thickness (mils.)	Min. DLB VAC	TEST FORCE (LB)		
33T0231-000	UNCOATED	-	-	-		
33T0231-00P	PARYLENE	0.5	1000	.30		
NOTES:						
Rev	Description				Date	INT
A	Original Draft				1995-4-10	JBE
B	UPDATE FORMAT RE-ACTIVATE PRINT REMOVE DBL-COATING SPECS				2005-10-4	JRK
C	REVISED TEMPLATE				2006-4-4	WMM
D						
E						
F						
G						
Date: 4/4/06	DWG #	33T0231-00P-C			Rev:	
Drawn By: WMM	Title #	33T0231-00P			C	
Steward This document contains information which is proprietary to Steward. No production or publication of this document in whole or in part shall be made without written authorization from Steward.						