

# PCN

## AO-PCN-2022-013-A

### Introduction of 2<sup>nd</sup> source for classic InGaAlP chip for TOPLED

01.07.2022

Dear Customer,

please review this **PCN** and provide your feedback in the **Customer approval form** (at the end of this PCN document) to your ams OSRAM sales partner before **05.08.2022** \*).

Please take note, that this PCN is published for the introduction of **additional source(s)**.

Your prompt reply will help ams OSRAM to assure a smooth and well executed transition. If ams OSRAM does not hear from your side by the due date, we will assume your (if you are a Distributor: and your customer's) full acceptance to this proposed change and its implementation.

ams OSRAM understands the time requirements your organization needs to approve this PCN. However, if you can provide ams OSRAM an estimated date your organization will have finalized this PCN review, ams OSRAM can use this date to plan continued production to secure your order needs during the expansion with additional source(s).

Your attention and response to this matter is highly appreciated.

**Please direct your inquiries to your local Sales office.**

\*) ams OSRAM aligns with the widely recognized JEDEC/ECIA/IPC Joint Standard No. 46, which stipulates:

- Customers should acknowledge receipt of the PCN within 30 days of delivery of the PCN.
- Lack of acknowledgement of the PCN within 30 days constitutes acceptance of the change.
- After acknowledgement, lack of additional response within the 90 day period constitutes acceptance of the change. If the customer requires additional time to perform sample testing, beyond the 90 day review period, an extension must be negotiated with the supplier.

<b>Subject of change:</b>	Introduction of 2 <sup>nd</sup> source for classic InGaAlP chip for TOPLED and additional location for released plater	
<b>Affected products:</b>	<b>Standard:</b> LS T676, LA T676, LO T676, LY T676, LG T676, LP T676 <b>Low current:</b> LS T67K, LO T67K, LY T67K, LG T67K <b>HOP:</b> LP T675	
<b>Reason for change:</b>	<ul style="list-style-type: none"> <li>• Secure continuous supply</li> <li>• Introduction of additional supplier chips</li> <li>• Introduction of additional production location of released plater</li> </ul>	
<b>Description of change:</b>	<u>Current status</u>	<u>New status</u>
	Inhouse chips	Inhouse chips + 2nd (and 3rd) source chips provided by supplier(s)
	Plater location: Wuxi/China	Plater location: Wuxi & Shanghai/China (same provider as currently)
	For details refer to file 2_cip_AO-PCN-2022-013-A	
<b>Time schedule for PCN material:</b> (after implementation of change):	Final qualification report:	01.08.2022
	Samples available:	01.07.2022 <sup>*)</sup> <small>*) For details refer to file 2_cip_AO-PCN-2022-013-A</small>
	Intended Start of delivery:	01.12.2022 <sup>**)</sup> <small>***) or earlier if released by customer and upon mutual agreement</small>
	Customer Review Finalization:	01.07.2023 <sup>***)</sup> <small>***) Expected final feedback of customer. Released order volume is related to deliveries of material from both previous and additional source(s).</small>
<b>Assessment:</b>	<b>No change in fit, form and reliability → no change in Datasheets</b>	
<b>Documentation:</b>	Customer information package 2_cip_AO-PCN-2022-013-A 3_cip_AO-PCN-2022-013-A_Qual	

**Note:**

Pre-PCN material: Products of current status, means before implementation of the changes as described in the PCN.

PCN material: Products with implementation of the changes as described in the PCN.

---

## Customer approval form AO-PCN-2022-013-A

### Introduction of 2<sup>nd</sup> source for classic InGaAlP chip for TOPLED

---

Please list product(s) affected in your application(s):

---

Please check the appropriate box below:

- |  |   |
|--|---|
| <input type="radio"/> <b>Approval:</b><br>We agree with the proposed change and accept start of the shipment upon availability of PCN material | <input type="radio"/> <b>Not relevant:</b><br>Change is not relevant for products in use. |
|--|---|

---

**Change cannot be accepted:**

- We have objections:**
- We request following Information:**
- We request following Samples:**
- Expected approval date:**
- Volume requirements for Pre-PCN material:**

---

**Remarks:**

---

**Sender:**

---

**Company:**

---

**Address / Location:**

---

**Signature:**

**Date:**

---

Please return this approval form to your Sales partner.

Published by ams-OSRAM AG  
Tobelbader Strasse 30, 8141 Premstaetten, Austria  
Phone +43 3136 500-0  
ams-osram.com © All rights reserved

PCN

AO-PCN-2022-013-A

Introduction of 2<sup>nd</sup> source for classic InGaAlP chip for TOPLED

Customer information package

S&MK EM FQE/OS Q CQM A ITR  
2022-07-01

# Agenda

	Page
1. Reason for change	3
2. Description of change	4-7
3. Changes in the datasheets	8
4. List of affected products	9
5. PCN samples	10
6. Time schedule	11

# AO-PCN-2022-013-A

## Introduction of 2<sup>nd</sup> source for classic InGaAlP chip for TOPLED





### Reason for change

Item	Description
1.	Secure continuous supply
2.	Introduction of additional supplier chips
3.	Introduction of additional production location of released plater

# AO-PCN-2022-013-A

## Introduction of 2<sup>nd</sup> source for classic InGaAlP chip for TOPLED

### Description of change for standard chips


Item	Current status	2 <sup>nd</sup> source chip A	2 <sup>nd</sup> source chip B	2 <sup>nd</sup> source chip C
Wafer size [mm]	100	100		
Wafer substrate	GaAs	GaAs		
Height [ $\mu\text{m}$ ]	220	180		
Chip dicing process	Sawing	Sawing		
Picture (schematic)				
Chip size [ $\mu\text{m}$ ]	200 x 200	200 x 200	180 x 180	180 x 180
Front metal type	Al	Au		
Front metal thickness [ $\mu\text{m}$ ]	1.5	2.25 - 2.9		
Back metal type	Au	Au		
Back metal thickness [ $\mu\text{m}$ ]	0.25	0.05 - 0.50		
Bond pad size [ $\mu\text{m}$ ]	100	100		



# AO-PCN-2022-013-A

## Introduction of 2<sup>nd</sup> source for classic InGaAlP chip for TOPLED



### Description of change for low current chips

Item	Current status	2 <sup>nd</sup> source chip D	2 <sup>nd</sup> source chip E
Wafer size [mm]	100	100	
Wafer substrate	GaAs	GaAs	
Height [ $\mu\text{m}$ ]	190	180	
Chip dicing process	Sawing	Sawing	
Picture (schematic)			
Chip size [ $\mu\text{m}$ ]	170 x 170	160 x 160	170 x 170
Front metal type	Al	Au	
Front metal thickness [ $\mu\text{m}$ ]	1.5	2.25-2.9	
Back metal type	Au	Au	
Back metal thickness [ $\mu\text{m}$ ]	0.25	0.35-0.50	
Bond pad size [ $\mu\text{m}$ ]	100	90	100

# AO-PCN-2022-013-A

## Introduction of 2<sup>nd</sup> source for classic InGaAlP chip for TOPLED

### Description of change for HOP Chip

Item	Current status	2 <sup>nd</sup> source chip F
Wafer size [mm]	100	100
Wafer substrate	GaAs	GaAs
Height [ $\mu\text{m}$ ]	220	220
Chip dicing process	Sawing	Sawing
Picture (schematic)		
Chip size [ $\mu\text{m}$ ]	300 x 300	300 x 300
Front metal type	Al	Au
Front metal thickness [ $\mu\text{m}$ ]	1.5	2.25
Back metal type	Au	Au
Back metal thickness [ $\mu\text{m}$ ]	0.25	0.35
Bond pad size [ $\mu\text{m}$ ]	110	100

# AO-PCN-2022-013-A

## Introduction of 2<sup>nd</sup> source for classic InGaAlP chip for TOPLED

### Description of change for all devices

Current status	New status
Plater location: Wuxi/China	Plater location: Wuxi & Shanghai/China (same provider as currently)

# AO-PCN-2022-013-A

## Introduction of 2<sup>nd</sup> source for classic InGaAlP chip for TOPLED

### Changes in the datasheets

No change in fit, form and function of affected devices → no change in Datasheets

# AO-PCN-2022-013-A

## Introduction of 2nd source for classic InGaAlP chip for TOPLED

### List of affected products

Brand	Standard	Low current	HOP
TOPLED	LS T676	LS T67K	LP T675
	LA T676	LO T67K	
	LO T676	LY T67K	
	LY T676	LG T67K	
	LG T676		
	LP T676		

Due to complexity not all device/chip source combinations will be available at start of series production.

# AO-PCN-2022-013-A

## Introduction of 2<sup>nd</sup> source for classic InGaAlP chip for TOPLED

### PCN Samples

Standard	Low current	HOP
LS T676	LS T67K	LP T675
LA T676	LO T67K	
LO T676	LY T67K	
LY T676	LG T67K	
LG T676		
LP T676		

Color code:  available     on request

# AO-PCN-2022-013-A

## Introduction of 2<sup>nd</sup> source for classic InGaAlP chip for TOPLED

### Time schedule

for PCN material ( <u>after</u> implementation of change):		
Final qualification report	01.08.2022	
Samples available	01.07.2022	
Intended Start of delivery	01.12.2022*)	*) or earlier if released by customer and upon mutual agreement
Customer Review Finalization:	01.07.2023 **)	***) Expected final feedback of customer. Released order volume is related to deliveries of material from both previous and additional source(s).

Note:

PCN material: Products with implementation of the changes as described in the PCN.

Sensing is life

am  OSRAM





# Qualification Results overview

# 220103C1

Subject	Qualification for 2nd source Chip introduction for classic InGaAlP TOPLED devices
Date	01.07.2022
Tested device	Chip A: LA T676; LY T676; LG T676; Chip B: LS T676; LY T676; LP T676; Chip C: LS T676; LO T676; LP T676; Chip D: LS T67K; LY T67K; LG T67K; Chip E: LS T67K; LY T67K; LG T67K; Chip F: LP T675
Brand (including sub brands)	TOPLED
Applies to	LA T676; LG T676; LO T676; LP T676; LS T676; LY T676; LG T67K; LO T67K; LS T67K; LY T67K; LP T675

Pre-conditioning according to Jedec Level II where applicable as per AEC-Q102 AEC-Q102 #A1 LA T676 (Chip A)

Test Performed	Condition	Duration	Sample Size	Failures		
				El.	Opt.	Vis
				<small>AEC-Q102 #E1</small>	<small>AEC-Q102 #E1</small>	<small>AEC-Q102 #E0</small>
Wet High Temperature Operating Life WHTOL1 <i>JESD22-A101</i> <small>AEC-Q102 #A2a Test PCB: IMS-AI</small>	$T_A = 85^\circ\text{C}; T_S = 100^\circ\text{C};$ $T_J = 105^\circ\text{C}; \text{r.H.} = 85\%$ $I_F = 30 \text{ mA}$ $T_{\text{on/off}} = 30 \text{ min}$	1000h	1x26	0	0	0
Wet High Temperature Operating Life WHTOL2 <i>JESD22-A101</i> <small>AEC-Q102 #A2b Test PCB: FR4</small>	$T_A = 85^\circ\text{C}; \text{r.H.} = 85\%$ $I_F = 5 \text{ mA}$	1000h	1x26	0	0	0
Powered Temperature Cycle PTC <i>JESD22-A105</i> <small>AEC-Q102 #A3a Test PCB: IMS-AI</small>	$T_A = -40^\circ\text{C}/+100^\circ\text{C}; T_S = 110^\circ\text{C};$ $T_J = 115^\circ\text{C}; I_F = 25 \text{ mA}$ $t_{\text{on/off}} = 5 \text{ min}$	1000c	1x26	0	0	0
Temperature Cycling TC <i>JESD22-A104</i> <small>AEC-Q102 #A4a Test PCB: FR4</small>	$T_A = -40^\circ\text{C}/+100^\circ\text{C}$ 15 min each extreme	1000c	1x26	0	0	0
High Temperature Operating Life HTOL <i>JESD22-A108</i> <small>AEC-Q102 #B1a Test PCB: IMS-AI</small>	$T_A = 100^\circ\text{C}; T_S = 110^\circ\text{C};$ $T_J = 120^\circ\text{C}; I_F = 30 \text{ mA}$	1000h	1x26	0	0	0
Pulsed Operating Life PLT <i>JESD22-A108</i> <small>AEC-Q102 #B3 Test PCB: FR4</small>	$T_A = 25^\circ\text{C}$ $I_F = 120 \text{ mA}; t_p = 0,1 \text{ ms};$ $D = 3\%$	1000h	1x26	0	0	0
Dew DEW <i>AEC-Q102-001</i> <small>AEC-Q102 #C7 Test PCB: FR4</small>	$T_{A,\text{min}} = 10^\circ\text{C}$ $T_{A,\text{max}} = 80^\circ\text{C}$ $\text{r.H.} = 53\text{-}100\%$ $I_F = 5 \text{ mA}$	10c	1x26	0	0	0
Solderability SD <i>IEC 60068-2-58</i> <small>AEC-Q102 #C10</small>	$T_A = 235^\circ\text{C}$ method 2 (reflow simulation)	1x	1x10	-	-	0
Hydrogen Sulphide H2S <i>IEC 60068-2-43</i> <small>AEC-Q102 #C12 Test PCB: FR4</small>	15 ppm H <sub>2</sub> S 40°C/90% r.H.	336h	1x26	0	0	0
Flowing Mixed Gas FMG <i>IEC 60068-2-60</i> <small>AEC-Q102 #C13 Test PCB: FR4</small>	$T_A = 25^\circ\text{C},$ $\text{r.H.} = 75\%$ Test method 4	500h	1x26	0	0	0
Board Flex Test BF <i>AEC-Q102-002</i> <small>AEC-Q102 #C14 Test PCB: FR4</small>	2 mm	1x	1x10	0	0	0
Electrostatic Discharge HBM <i>ANSI/ESDA/ JEDEC JS-001</i> <small>AEC-Q102 #E3 Test PCB: FR4</small>	Human Body Model	2000V	1x10	0	0	0

Constant Acceleration CA	<i>MIL-STD-750-2</i> AEC-Q102 #G1	Method 2006 2000 gf; 1 min in x/y/z (+/- direction)	1x	3x10	
Vibration Variable Frequency VVF	<i>JESD22-B103</i> AEC-Q102 #G2	20g, 20-2000Hz; 4min / cy; 4cy/axis service condition 1	1x	sequential samples	for uncasted packages only
Mechanical Shock MS	<i>JESD22-B110</i> AEC-Q102 #G3	1500g for 0.5ms, 5 blows, 3 orientations	1x	sequential samples	
Hermeticity HER	<i>JESD22-A109</i> AEC-Q102 #G4	Leak Test: Fine & Gross	1x	sequential samples	

### Additional Tests to AEC Q102

Test Performed	Condition	Duration	Sample Size	Failures		
				El.	Opt.	Vis
Electrostatic Discharge MM	<i>JESD22-A115</i> Machine Model Test PCB: FR4	200V	1x10	0	0	0

### LA T676:

#### Failure criteria:

Electrical failures:  $V_f$  ( $I_f = 20\text{mA}$ ) > 2,33 V;  $\pm 10\%$  from initial value

Optical failures:  $I_v$  ( $I_f = 20\text{mA}$ ) absolute limit:  $\pm 50\%$  max.  
 $\lambda_{\text{dom}}$  ( $I_f = 20\text{mA}$ )  $\pm 2\text{nm}$  from initial value

Visual failures: acc JEDEC JESD22-B101

**Conclusion: The tested devices representing the product family as stated in the applies to section fulfill the reliability requirements of AEC-Q102 Rev-A.**

Pre-conditioning according to Jedec Level II where applicable as per AEC-Q102 AEC-Q102 #A1 LY T676 (Chip A)

Test Performed	Condition	Duration	Sample Size	Failures			
				El.	Opt.	Vis	
				<small>AEC-Q102 #E1</small>	<small>AEC-Q102 #E1</small>	<small>AEC-Q102 #E0</small>	
Wet High Temperature Operating Life WHTOL1	<i>JESD22-A101</i> <small>AEC-Q102 #A2a</small> Test PCB: IMS-AI	$T_A = 85^\circ\text{C}; T_S = 105^\circ\text{C};$ $T_J = 110^\circ\text{C}; r.H. = 85\%$ $I_F = 30 \text{ mA}$ $T_{\text{on/off}} = 30 \text{ min}$	1000h	1x26	0	0	0
Wet High Temperature Operating Life WHTOL2	<i>JESD22-A101</i> <small>AEC-Q102 #A2b</small> Test PCB: FR4	$T_A = 85^\circ\text{C}; r.H. = 85\%$ $I_F = 5 \text{ mA}$	1000h	1x26	0	0	0
Powered Temperature Cycle PTC	<i>JESD22-A105</i> <small>AEC-Q102 #A3a</small> Test PCB: IMS-AI	$T_A = -40^\circ\text{C}/+100^\circ\text{C}; T_S = 100^\circ\text{C};$ $T_J = 105^\circ\text{C}; I_F = 5 \text{ mA}$ $t_{\text{on/off}} = 5 \text{ min}$	1000c	1x26	0	0	0
Temperature Cycling TC	<i>JESD22-A104</i> <small>AEC-Q102 #A4a</small> Test PCB: FR4	$T_A = -40^\circ\text{C}/+100^\circ\text{C}$ 15 min each extreme	1000c	1x26	0	0	0
High Temperature Operating Life HTOL	<i>JESD22-A108</i> <small>AEC-Q102 #B1a</small> Test PCB: IMS-AI	$T_A = 85^\circ\text{C}; T_S = 105^\circ\text{C};$ $T_J = 110^\circ\text{C}; I_F = 30 \text{ mA}$	1000h	1x26	0	0	0
Pulsed Operating Life PLT	<i>JESD22-A108</i> <small>AEC-Q102 #B3</small> Test PCB: FR4	$T_A = 25^\circ\text{C}$ $I_F = 200 \text{ mA}; t_p = 0,1 \text{ ms};$ $D = 3\%$	1000h	1x26	0	0	0
Dew DEW	<i>AEC-Q102-001</i> <small>AEC-Q102 #C7</small> Test PCB: FR4	$T_{A,\text{min}} = 10^\circ\text{C}$ $T_{A,\text{max}} = 80^\circ\text{C}$ $r.H. = 53-100\%$ $I_F = 5 \text{ mA}$	10c	1x26	0	0	0
Solderability SD	<i>IEC 60068-2-58</i> <small>AEC-Q102 #C10</small>	$T_A = 235^\circ\text{C}$ method 2 (reflow simulation)	1x	1x10	-	-	0
Hydrogen Sulphide H2S	<i>IEC 60068-2-43</i> <small>AEC-Q102 #C12</small> Test PCB: FR4	15 ppm H <sub>2</sub> S 40°C/90%r.H.	336h	1x26	0	0	0
Flowing Mixed Gas FMG	<i>IEC 60068-2-60</i> <small>AEC-Q102 #C13</small> Test PCB: FR4	$T_A = 25^\circ\text{C},$ $r.H. = 75\%$ Test method 4	500h	1x26	0	0	0
Board Flex Test BF	<i>AEC-Q102-002</i> <small>AEC-Q102 #C14</small> Test PCB: FR4	2 mm	1x	1x10	0	0	0
Electrostatic Discharge HBM	<i>ANSI/ESDA/ JEDEC JS-001</i> <small>AEC-Q102 #E3</small> Test PCB: FR4	Human Body Model	2000V	1x10	0	0	0

Constant Acceleration CA	<i>MIL-STD-750-2</i> AEC-Q102 #G1	Method 2006 2000 gf; 1 min in x/y/z (+/- direction)	1x	1x10	
Vibration Variable Frequency VVF	<i>JESD22-B103</i> AEC-Q102 #G2	20g, 20-2000Hz; 4min / cy; 4cy/axis service condition 1	1x	sequential samples	for uncasted packages only
Mechanical Shock MS	<i>JESD22-B110</i> AEC-Q102 #G3	1500g for 0.5ms, 5 blows, 3 orientations	1x	sequential samples	
Hermeticity HER	<i>JESD22-A109</i> AEC-Q102 #G4	Leak Test: Fine & Gross	1x	sequential samples	

### Additional Tests to AEC Q102

Test Performed	Condition	Duration	Sample Size	Failures			
				El.	Opt.	Vis	
Electrostatic Discharge MM	<i>JESD22-A115</i> Test PCB: FR4	Machine Model	200V	2x10	0	0	0

### LY T676:

#### Failure criteria:

Electrical failures:  $V_f$  ( $I_f=20$  mA) > 2,4V;  $\pm 10\%$  from initial value

Optical failures:  $I_v$  ( $I_f=20$  mA) absolute limit:  $\pm 50\%$  max.  
 $\lambda_{dom}$  ( $I_f=20$  mA)  $\pm 2$  nm from initial value

Visual failures: acc JEDEC JESD22-B101

**Conclusion: The tested devices representing the product family as stated in the applies to section fulfill the reliability requirements of AEC-Q102 Rev-A.**

Pre-conditioning according to Jedec Level II where applicable as per AEC-Q102 AEC-Q102 #A1 **LG T676 (Chip A)**

Test Performed	Condition	Duration	Sample Size	Failures		
				El.	Opt.	Vis
				<small>AEC-Q102 #E1</small>	<small>AEC-Q102 #E1</small>	<small>AEC-Q102 #E0</small>
Wet High Temperature Operating Life WHTOL1 <i>JESD22-A101</i> <small>AEC-Q102 #A2a Test PCB: IMS-AI</small>	$T_A = 85^{\circ}\text{C}; T_S = 105^{\circ}\text{C};$ $T_J = 110^{\circ}\text{C}; r.H. = 85\%$ $I_F = 30 \text{ mA}$ $T_{\text{on/off}} = 30 \text{ min}$	1000h	1x26	0	0	0
Wet High Temperature Operating Life WHTOL2 <i>JESD22-A101</i> <small>AEC-Q102 #A2b Test PCB: FR4</small>	$T_A = 85^{\circ}\text{C}; r.H. = 85\%$ $I_F = 5 \text{ mA}$	1000h	1x26	0	0	0
Powered Temperature Cycle PTC <i>JESD22-A105</i> <small>AEC-Q102 #A3a Test PCB: IMS-AI</small>	$T_A = -40^{\circ}\text{C}/+100^{\circ}\text{C}; T_S = 100^{\circ}\text{C};$ $T_J = 105^{\circ}\text{C}; I_F = 5 \text{ mA}$ $t_{\text{on/off}} = 5 \text{ min}$	1000c	1x26	0	0	0
Temperature Cycling TC <i>JESD22-A104</i> <small>AEC-Q102 #A4a Test PCB: FR4</small>	$T_A = -40^{\circ}\text{C}/+100^{\circ}\text{C}$ 15 min each extreme	1000c	1x26	0	0	0
High Temperature Operating Life HTOL <i>JESD22-A108</i> <small>AEC-Q102 #B1a Test PCB: IMS-AI</small>	$T_A = 100^{\circ}\text{C}; T_S = 110^{\circ}\text{C};$ $T_J = 125^{\circ}\text{C}; I_F = 30 \text{ mA}$	1000h	1x26	0	0	0
Pulsed Operating Life PLT <i>JESD22-A108</i> <small>AEC-Q102 #B3 Test PCB: FR4</small>	$T_A = 25^{\circ}\text{C}$ $I_F = 120 \text{ mA}; t_p = 0,1 \text{ ms};$ $D = 3\%$	1000h	1x26	0	0	0
Dew DEW <i>AEC-Q102-001</i> <small>AEC-Q102#C7 Test PCB: FR4</small>	$T_{A,\text{min}} = 10^{\circ}\text{C}$ $T_{A,\text{max}} = 80^{\circ}\text{C}$ $r.H. = 53-100\%$ $I_F = 5 \text{ mA}$	10c	1x26	0	0	0
Solderability SD <i>IEC 60068-2-58</i> <small>AEC-Q102 #C10</small>	$T_A = 235^{\circ}\text{C}$ method 2 (reflow simulation)	1x	1x10	-	-	0
Hydrogen Sulphide H2S <i>IEC 60068-2-43</i> <small>AEC-Q102 #C12 Test PCB: FR4</small>	15 ppm H <sub>2</sub> S 40°C/90%r.H.	336h	1x26	0	0	0
Flowing Mixed Gas FMG <i>IEC 60068-2-60</i> <small>AEC-Q102 #C13 Test PCB: FR4</small>	$T_A = 25^{\circ}\text{C},$ $r.H. = 75\%$ Test method 4	500h	1x26	0	0	0
Board Flex Test BF <i>AEC-Q102-002</i> <small>AEC-Q102 #C14 Test PCB: FR4</small>	2 mm	1x	1x10	0	0	0
Electrostatic Discharge HBM <i>ANSI/ESDA/ JEDEC JS-001</i> <small>AEC-Q102 #E3 Test PCB: FR4</small>	Human Body Model	2000V	1x10	0	0	0

Constant Acceleration CA	<i>MIL-STD-750-2</i> AEC-Q102 #G1	Method 2006 2000 gf; 1 min in x/y/z (+/- direction)	1x	3x10	
Vibration Variable Frequency VVF	<i>JESD22-B103</i> AEC-Q102 #G2	20g, 20-2000Hz; 4min / cy; 4cy/axis service condition 1	1x	sequential samples	for uncasted packages only
Mechanical Shock MS	<i>JESD22-B110</i> AEC-Q102 #G3	1500g for 0.5ms, 5 blows, 3 orientations	1x	sequential samples	
Hermeticity HER	<i>JESD22-A109</i> AEC-Q102 #G4	Leak Test: Fine & Gross	1x	sequential samples	

### Additional Tests to AEC Q102

Test Performed	Condition	Duration	Sample Size	Failures		
				El.	Opt.	Vis
Electrostatic Discharge MM	<i>JESD22-A115</i> Machine Model Test PCB: FR4	200V	1x10	0	0	0

### LG T676:

#### Failure criteria:

Electrical failures:  $V_f (I_f = 20\text{mA})$  > 2,4V;  $\pm 10\%$  from initial value

Optical failures:  $I_v (I_f = 20\text{mA})$  absolute limit:  $\pm 50\%$  max.  
 $\lambda_{\text{dom}} (I_f = 20\text{mA})$   $\pm 2$  nm from initial value

Visual failures: acc JEDEC JESD22-B101

**Conclusion: The tested devices representing the product family as stated in the applies to section fulfill the reliability requirements of AEC-Q102 Rev-A.**

Pre-conditioning according to Jedec Level II where applicable as per AEC-Q102 AEC-Q102 #A1 **LS T676 (Chip B)**

Test Performed	Condition	Duration	Sample Size	Failures		
				El.	Opt.	Vis
				<small>AEC-Q102 #E1</small>	<small>AEC-Q102 #E1</small>	<small>AEC-Q102 #E0</small>
Wet High Temperature Operating Life WHTOL1 <i>JESD22-A101</i> <small>AEC-Q102 #A2a Test PCB: IMS-AI</small>	$T_A = 85^\circ\text{C}; T_S = 100^\circ\text{C};$ $T_J = 110^\circ\text{C}; \text{r.H.} = 85\%$ $I_F = 30 \text{ mA}$ $T_{\text{on/off}} = 30 \text{ min}$	1000h	1x26	0	0	0
Wet High Temperature Operating Life WHTOL2 <i>JESD22-A101</i> <small>AEC-Q102 #A2b Test PCB: FR4</small>	$T_A = 85^\circ\text{C}; \text{r.H.} = 85\%$ $I_F = 5 \text{ mA}$	1000h	1x26	0	0	0
Powered Temperature Cycle PTC <i>JESD22-A105</i> <small>AEC-Q102 #A3a Test PCB: IMS-AI</small>	$T_A = -40^\circ\text{C}/+85^\circ\text{C}; T_S = 100^\circ\text{C};$ $T_J = 105^\circ\text{C}; I_F = 30 \text{ mA}$ $t_{\text{on/off}} = 5 \text{ min}$	1000c	1x26	0	0	0
Temperature Cycling TC <i>JESD22-A104</i> <small>AEC-Q102 #A4a Test PCB: FR4</small>	$T_A = -40^\circ\text{C}/+100^\circ\text{C}$ 15 min each extreme	1000c	1x26	0	0	0
High Temperature Operating Life HTOL <i>JESD22-A108</i> <small>AEC-Q102 #B1a Test PCB: IMS-AI</small>	$T_A = 85^\circ\text{C}; T_S = 100^\circ\text{C};$ $T_J = 110^\circ\text{C}; I_F = 30 \text{ mA}$	1000h	1x26	0	0	0
Pulsed Operating Life PLT <i>JESD22-A108</i> <small>AEC-Q102 #B3 Test PCB: FR4</small>	$T_A = 25^\circ\text{C}$ $I_F = 100 \text{ mA}; t_p = 0,1 \text{ ms};$ $D = 3\%$	1000h	1x26	0	0	0
Dew DEW <i>AEC-Q102-001</i> <small>AEC-Q102 #C7 Test PCB: FR4</small>	$T_{A,\text{min}} = 10^\circ\text{C}$ $T_{A,\text{max}} = 80^\circ\text{C}$ $\text{r.H.} = 53\text{-}100\%$ $I_F = 5 \text{ mA}$	10c	1x26	0	0	0
Solderability SD <i>IEC 60068-2-58</i> <small>AEC-Q102 #C10</small>	$T_A = 235^\circ\text{C}$ method 2 (reflow simulation)	1x	1x10	-	-	0
Hydrogen Sulphide H2S <i>IEC 60068-2-43</i> <small>AEC-Q102 #C12 Test PCB: FR4</small>	15 ppm H <sub>2</sub> S 40°C/90% r.H.	336h	1x26	0	0	0
Flowing Mixed Gas FMG <i>IEC 60068-2-60</i> <small>AEC-Q102 #C13 Test PCB: FR4</small>	$T_A = 25^\circ\text{C},$ $\text{r.H.} = 75\%$ Test method 4	500h	1x26	0	0	0
Board Flex Test BF <i>AEC-Q102-002</i> <small>AEC-Q102 #C14 Test PCB: FR4</small>	2mm	1x	1x10	0	0	0
Electrostatic Discharge HBM <i>ANSI/ESDA/ JEDEC JS-001</i> <small>AEC-Q102 #E3 Test PCB: FR4</small>	Human Body Model	2000V	1x10	0	0	0



Constant Acceleration CA	<i>MIL-STD-750-2</i> AEC-Q102 #G1	Method 2006 2000 gf; 1 min in x/y/z (+/- direction)	1x	1x10	
Vibration Variable Frequency VVF	<i>JESD22-B103</i> AEC-Q102 #G2	20g, 20-2000Hz; 4min / cy; 4cy/axis service condition 1	1x	sequential samples	for uncasted packages only
Mechanical Shock MS	<i>JESD22-B110</i> AEC-Q102 #G3	1500g for 0.5ms, 5 blows, 3 orientations	1x	sequential samples	
Hermeticity HER	<i>JESD22-A109</i> AEC-Q102 #G4	Leak Test: Fine & Gross	1x	sequential samples	

### Additional Tests to AEC Q102

Test Performed	Condition	Duration	Sample Size	Failures			
				El.	Opt.	Vis	
Electrostatic Discharge MM	<i>JESD22-A115</i> Test PCB: FR4	Machine Model	200V	2x10	0	0	0

### LS T676:

#### Failure criteria:

Electrical failures:  $V_f$  ( $I_f = 20$  mA) > 2,3V;  $\pm 10\%$  from initial value

Optical failures:  $I_v$  ( $I_f = 20$  mA) absolute limit:  $\pm 50\%$  max.  
 $\lambda_{dom}$  ( $I_f = 20$  mA)  $\pm 2$  nm from initial value

Visual failures: acc JEDEC JESD22-B101

**Conclusion: The tested devices representing the product family as stated in the applies to section fulfill the reliability requirements of AEC-Q102 Rev-A.**

Pre-conditioning according to Jedec Level II where applicable as per AEC-Q102 AEC-Q102 #A1 LY T676 (Chip B)

Test Performed	Condition	Duration	Sample Size	Failures		
				El.	Opt.	Vis
				<small>AEC-Q102 #E1</small>	<small>AEC-Q102 #E1</small>	<small>AEC-Q102 #E0</small>
Wet High Temperature Operating Life WHTOL1 <i>JESD22-A101</i> <small>AEC-Q102 #A2a Test PCB: IMS-AI</small>	$T_A = 85^\circ\text{C}; T_S = 100^\circ\text{C};$ $T_J = 110^\circ\text{C}; \text{r.H.} = 85\%$ $I_F = 30 \text{ mA}$ $T_{\text{on/off}} = 30 \text{ min}$	1000h	1x26	0	0	0
Wet High Temperature Operating Life WHTOL2 <i>JESD22-A101</i> <small>AEC-Q102 #A2b Test PCB: FR4</small>	$T_A = 85^\circ\text{C}; \text{r.H.} = 85\%$ $I_F = 5 \text{ mA}$	1000h	1x26	0	0	0
Powered Temperature Cycle PTC <i>JESD22-A105</i> <small>AEC-Q102 #A3a Test PCB: IMS-AI</small>	$T_A = -40^\circ\text{C}/+100^\circ\text{C}; T_S = 100^\circ\text{C};$ $T_J = 105^\circ\text{C}; I_F = 5 \text{ mA}$ $t_{\text{on/off}} = 5 \text{ min}$	1000c	1x26	0	0	0
Temperature Cycling TC <i>JESD22-A104</i> <small>AEC-Q102 #A4a Test PCB: FR4</small>	$T_A = -40^\circ\text{C}/+100^\circ\text{C}$ 15 min each extreme	1000c	1x26	0	0	0
High Temperature Operating Life HTOL <i>JESD22-A108</i> <small>AEC-Q102 #B1a Test PCB: IMS-AI</small>	$T_A = 85^\circ\text{C}; T_S = 100^\circ\text{C};$ $T_J = 110^\circ\text{C}; I_F = 30 \text{ mA}$	1000h	1x26	0	0	0
Pulsed Operating Life PLT <i>JESD22-A108</i> <small>AEC-Q102 #B3 Test PCB: FR4</small>	$T_A = 25^\circ\text{C}$ $I_F = 200 \text{ mA}; t_p = 0,1 \text{ ms};$ $D = 3\%$	1000h	1x26	0	0	0
Dew DEW <i>AEC-Q102-001</i> <small>AEC-Q102 #C7 Test PCB: FR4</small>	$T_{A,\text{min}} = 10^\circ\text{C}$ $T_{A,\text{max}} = 80^\circ\text{C}$ $\text{r.H.} = 53-100\%$ $I_F = 5 \text{ mA}$	10c	1x26	0	0	0
Solderability SD <i>IEC 60068-2-58</i> <small>AEC-Q102 #C10</small>	$T_A = 235^\circ\text{C}$ method 2 (reflow simulation)	1x	1x10	-	-	0
Hydrogen Sulphide H2S <i>IEC 60068-2-43</i> <small>AEC-Q102 #C12 Test PCB: FR4</small>	15 ppm H <sub>2</sub> S 40°C/90%r.H.	336h	1x26	0	0	0
Flowing Mixed Gas FMG <i>IEC 60068-2-60</i> <small>AEC-Q102 #C13 Test PCB: FR4</small>	$T_A = 25^\circ\text{C},$ $\text{r.H.} = 75\%$ Test method 4	500h	1x26	0	0	0
Board Flex Test BF <i>AEC-Q102-002</i> <small>AEC-Q102 #C14 Test PCB: FR4</small>	2 mm	1x	1x10	0	0	0
Electrostatic Discharge HBM <i>ANSI/ESDA/ JEDEC JS-001</i> <small>AEC-Q102 #E3 Test PCB: FR4</small>	Human Body Model	2000V	1x10	0	0	0

Constant Acceleration CA	<i>MIL-STD-750-2</i> AEC-Q102 #G1	Method 2006 2000 gf; 1 min in x/y/z (+/- direction)	1x	1x10	
Vibration Variable Frequency VVF	<i>JESD22-B103</i> AEC-Q102 #G2	20g, 20-2000Hz; 4min / cy; 4cy/axis service condition 1	1x	sequential samples	for uncasted packages only
Mechanical Shock MS	<i>JESD22-B110</i> AEC-Q102 #G3	1500g for 0.5ms, 5 blows, 3 orientations	1x	sequential samples	
Hermeticity HER	<i>JESD22-A109</i> AEC-Q102 #G4	Leak Test: Fine & Gross	1x	sequential samples	

### Additional Tests to AEC Q102

Test Performed	Condition	Duration	Sample Size	Failures			
				El.	Opt.	Vis	
Electrostatic Discharge MM	<i>JESD22-A115</i> Test PCB: FR4	Machine Model	200V	2x10	0	0	0

### LY T676:

#### Failure criteria:

Electrical failures:  $V_f$  ( $I_f=20$  mA) > 2,4V;  $\pm 10\%$  from initial value

Optical failures:  $I_v$  ( $I_f=20$  mA) absolute limit:  $\pm 50\%$  max.  
 $\lambda_{dom}$  ( $I_f=20$  mA)  $\pm 2$  nm from initial value

Visual failures: acc JEDEC JESD22-B101

**Conclusion: The tested devices representing the product family as stated in the applies to section fulfill the reliability requirements of AEC-Q102 Rev-A.**

Pre-conditioning according to Jedec Level II where applicable as per AEC-Q102 AEC-Q102 #A1 LP T676 (Chip B)

Test Performed	Condition	Duration	Sample Size	Failures		
				El.	Opt.	Vis
				<small>AEC-Q102 #E1</small>	<small>AEC-Q102 #E1</small>	<small>AEC-Q102 #E0</small>
Wet High Temperature Operating Life WHTOL1 <i>JESD22-A101</i> <small>AEC-Q102 #A2a Test PCB: IMS-AI</small>	$T_A = 85^\circ\text{C}; T_S = 100^\circ\text{C};$ $T_J = 115^\circ\text{C}; \text{r.H.} = 85\%$ $I_F = 30 \text{ mA}$ $T_{\text{on/off}} = 30 \text{ min}$	1000h	1x26	0	0	0
Wet High Temperature Operating Life WHTOL2 <i>JESD22-A101</i> <small>AEC-Q102 #A2b Test PCB: FR4</small>	$T_A = 85^\circ\text{C}; \text{r.H.} = 85\%$ $I_F = 5 \text{ mA}$	1000h	1x26	0	0	0
Powered Temperature Cycle PTC <i>JESD22-A105</i> <small>AEC-Q102 #A3a Test PCB: IMS-AI</small>	$T_A = -40^\circ\text{C}/+85^\circ\text{C}; T_S = 100^\circ\text{C};$ $T_J = 105^\circ\text{C}; I_F = 30 \text{ mA}$ $t_{\text{on/off}} = 5 \text{ min}$	1000c	1x26	0	0	0
Temperature Cycling TC <i>JESD22-A104</i> <small>AEC-Q102 #A4a Test PCB: FR4</small>	$T_A = -40^\circ\text{C}/+100^\circ\text{C}$ 15 min each extreme	1000c	1x26	0	0	0
High Temperature Operating Life HTOL <i>JESD22-A108</i> <small>AEC-Q102 #B1a Test PCB: IMS-AI</small>	$T_A = 85^\circ\text{C}; T_S = 100^\circ\text{C};$ $T_J = 115^\circ\text{C}; I_F = 30 \text{ mA}$	1000h	1x26	0	0	0
Pulsed Operating Life PLT <i>JESD22-A108</i> <small>AEC-Q102 #B3 Test PCB: FR4</small>	$T_A = 25^\circ\text{C}$ $I_F = 50 \text{ mA}; t_p = 0,1 \text{ ms};$ $D = 3\%$	1000h	1x26	0	0	0
Dew DEW <i>AEC-Q102-001</i> <small>AEC-Q102 #C7 Test PCB: FR4</small>	$T_{A,\text{min}} = 10^\circ\text{C}$ $T_{A,\text{max}} = 80^\circ\text{C}$ $\text{r.H.} = 53\text{-}100\%$ $I_F = 5 \text{ mA}$	10c	1x26	0	0	0
Solderability SD <i>IEC 60068-2-58</i> <small>AEC-Q102 #C10</small>	$T_A = 235^\circ\text{C}$ method 2 (reflow simulation)	1x	1x10	-	-	0
Hydrogen Sulphide H2S <i>IEC 60068-2-43</i> <small>AEC-Q102 #C12 Test PCB: FR4</small>	15 ppm H <sub>2</sub> S 40°C/90% r.H.	336h	1x26	0	0	0
Flowing Mixed Gas FMG <i>IEC 60068-2-60</i> <small>AEC-Q102 #C13 Test PCB: FR4</small>	$T_A = 25^\circ\text{C},$ $\text{r.H.} = 75\%$ Test method 4	500h	1x26	0	0	0
Board Flex Test BF <i>AEC-Q102-002</i> <small>AEC-Q102 #C14 Test PCB: FR4</small>	2 mm	1x	1x10	0	0	0
Electrostatic Discharge HBM <i>ANSI/ESDA/ JEDEC JS-001</i> <small>AEC-Q102 #E3 Test PCB: FR4</small>	Human Body Model	2000V	1x10	0	0	0

Constant Acceleration CA	<i>MIL-STD-750-2</i> AEC-Q102 #G1	Method 2006 2000 gf; 1 min in x/y/z (+/- direction)	1x	1x10	
Vibration Variable Frequency VVF	<i>JESD22-B103</i> AEC-Q102 #G2	20g, 20-2000Hz; 4min / cy; 4cy/axis service condition 1	1x	sequential samples	for uncasted packages only
Mechanical Shock MS	<i>JESD22-B110</i> AEC-Q102 #G3	1500g for 0.5ms, 5 blows, 3 orientations	1x	sequential samples	
Hermeticity HER	<i>JESD22-A109</i> AEC-Q102 #G4	Leak Test: Fine & Gross	1x	sequential samples	

### Additional Tests to AEC Q102

Test Performed	Condition	Duration	Sample Size	Failures		
				El.	Opt.	Vis
Electrostatic Discharge MM	<i>JESD22-A115</i> Machine Model Test PCB: FR4	200V	1x10	0	0	0

### LP T676:

#### Failure criteria:

Electrical failures:	$V_f$ ( $I_f = 20$ mA)	$> 2,4V; \pm 10\%$ from initial value
Optical failures:	$I_v$ ( $I_f = 20$ mA) $\lambda_{dom}$ ( $I_f = 20$ mA)	absolute limit: $\pm 50\%$ max. $\pm 2$ nm from initial value
Visual failures:	acc JEDEC JESD22-B101	

**Conclusion: The tested devices representing the product family as stated in the applies to section fulfill the reliability requirements of AEC-Q102 Rev-A.**

Pre-conditioning according to Jedec Level II where applicable as per AEC-Q102 AEC-Q102 #A1 **LS T676 (Chip C)**

Test Performed	Condition	Duration	Sample Size	Failures		
				El.	Opt.	Vis
				<small>AEC-Q102 #E1</small>	<small>AEC-Q102 #E1</small>	<small>AEC-Q102 #E0</small>
Wet High Temperature Operating Life WHTOL1 <i>JESD22-A101</i> <small>AEC-Q102 #A2a Test PCB: IMS-AI</small>	$T_A = 85^\circ\text{C}; T_S = 100^\circ\text{C};$ $T_J = 110^\circ\text{C}; \text{r.H.} = 85\%$ $I_F = 30 \text{ mA}$ $T_{\text{on/off}} = 30 \text{ min}$	1000h	1x26	0	0	0
Wet High Temperature Operating Life WHTOL2 <i>JESD22-A101</i> <small>AEC-Q102 #A2b Test PCB: FR4</small>	$T_A = 85^\circ\text{C}; \text{r.H.} = 85\%$ $I_F = 5 \text{ mA}$	1000h	1x26	0	0	0
Powered Temperature Cycle PTC <i>JESD22-A105</i> <small>AEC-Q102 #A3a Test PCB: IMS-AI</small>	$T_A = -40^\circ\text{C}/+85^\circ\text{C}; T_S = 100^\circ\text{C};$ $T_J = 110^\circ\text{C}; I_F = 30 \text{ mA}$ $t_{\text{on/off}} = 5 \text{ min}$	1000c	1x26	0	0	0
Temperature Cycling TC <i>JESD22-A104</i> <small>AEC-Q102 #A4a Test PCB: FR4</small>	$T_A = -40^\circ\text{C}/+100^\circ\text{C}$ 15 min each extreme	1000c	1x26	0	0	0
High Temperature Operating Life HTOL <i>JESD22-A108</i> <small>AEC-Q102 #B1a Test PCB: IMS-AI</small>	$T_A = 85^\circ\text{C}; T_S = 100^\circ\text{C};$ $T_J = 110^\circ\text{C}; I_F = 30 \text{ mA}$	1000h	1x26	0	0	0
Pulsed Operating Life PLT <i>JESD22-A108</i> <small>AEC-Q102 #B3 Test PCB: FR4</small>	$T_A = 25^\circ\text{C}$ $I_F = 120 \text{ mA}; t_p = 0,1 \text{ ms};$ $D = 3\%$	1000h	1x26	0	0	0
Dew DEW <i>AEC-Q102-001</i> <small>AEC-Q102 #C7 Test PCB: FR4</small>	$T_{A,\text{min}} = 10^\circ\text{C}$ $T_{A,\text{max}} = 80^\circ\text{C}$ $\text{r.H.} = 53\text{-}100\%$ $I_F = 5 \text{ mA}$	10c	1x26	0	0	0
Solderability SD <i>IEC 60068-2-58</i> <small>AEC-Q102 #C10</small>	$T_A = 235^\circ\text{C}$ method 2 (reflow simulation)	1x	1x10	-	-	0
Hydrogen Sulphide H2S <i>IEC 60068-2-43</i> <small>AEC-Q102 #C12 Test PCB: FR4</small>	15 ppm H <sub>2</sub> S 40°C/90% r.H.	336h	1x26	0	0	0
Flowing Mixed Gas FMG <i>IEC 60068-2-60</i> <small>AEC-Q102 #C13 Test PCB: FR4</small>	$T_A = 25^\circ\text{C},$ $\text{r.H.} = 75\%$ Test method 4	500h	1x26	0	0	0
Board Flex Test BF <i>AEC-Q102-002</i> <small>AEC-Q102 #C14 Test PCB: FR4</small>	2 mm	1x	1x10	0	0	0
Electrostatic Discharge HBM <i>ANSI/ESDA/ JEDEC JS-001</i> <small>AEC-Q102 #E3 Test PCB: FR4</small>	Human Body Model	2000V	1x10	0	0	0

Constant Acceleration CA	<i>MIL-STD-750-2</i> AEC-Q102 #G1	Method 2006 2000 gf; 1 min in x/y/z (+/- direction)	1x	1x10	
Vibration Variable Frequency VVF	<i>JESD22-B103</i> AEC-Q102 #G2	20g, 20-2000Hz; 4min / cy; 4cy/axis service condition 1	1x	sequential samples	for uncasted packages only
Mechanical Shock MS	<i>JESD22-B110</i> AEC-Q102 #G3	1500g for 0.5ms, 5 blows, 3 orientations	1x	sequential samples	
Hermeticity HER	<i>JESD22-A109</i> AEC-Q102 #G4	Leak Test: Fine & Gross	1x	sequential samples	

### Additional Tests to AEC Q102

Test Performed	Condition	Duration	Sample Size	Failures			
				El.	Opt.	Vis	
Electrostatic Discharge MM	<i>JESD22-A115</i> Test PCB: FR4	Machine Model	200V	2x10	0	0	0

### LS T676:

#### Failure criteria:

Electrical failures:	$V_f (I_f = 20 \text{ mA})$	$> 2,3V; \pm 10\%$ from initial value
Optical failures:	$I_v (I_f = 20 \text{ mA})$ $\lambda_{\text{dom}} (I_f = 20 \text{ mA})$	absolute limit: $\pm 50\%$ max. $\pm 2 \text{ nm}$ from initial value
Visual failures:	acc JEDEC JESD22-B101	

**Conclusion: The tested devices representing the product family as stated in the applies to section fulfill the reliability requirements of AEC-Q102 Initial/Rev-A.**

Pre-conditioning according to Jedec Level II where applicable as per AEC-Q102 AEC-Q102 #A1 **LO T676 (Chip C)**

Test Performed	Condition	Duration	Sample Size	Failures		
				El.	Opt.	Vis
				<small>AEC-Q102 #E1</small>	<small>AEC-Q102 #E1</small>	<small>AEC-Q102 #E0</small>
Wet High Temperature Operating Life WHTOL1 <i>JESD22-A101</i> <small>AEC-Q102 #A2a Test PCB: IMS-AI</small>	$T_A = 85^\circ\text{C}; T_S = 100^\circ\text{C};$ $T_J = 110^\circ\text{C}; \text{r.H.} = 85\%$ $I_F = 30 \text{ mA}$ $T_{\text{on/off}} = 30 \text{ min}$	1000h	1x26	0	0	0
Wet High Temperature Operating Life WHTOL2 <i>JESD22-A101</i> <small>AEC-Q102 #A2b Test PCB: FR4</small>	$T_A = 85^\circ\text{C}; \text{r.H.} = 85\%$ $I_F = 5 \text{ mA}$	1000h	1x26	0	0	0
Powered Temperature Cycle PTC <i>JESD22-A105</i> <small>AEC-Q102 #A3a Test PCB: IMS-AI</small>	$T_A = -40^\circ\text{C}/+100^\circ\text{C}; T_S = 100^\circ\text{C};$ $T_J = 105^\circ\text{C}; I_F = 5 \text{ mA}$ $t_{\text{on/off}} = 5 \text{ min}$	1000c	1x26	0	0	0
Temperature Cycling TC <i>JESD22-A104</i> <small>AEC-Q102 #A4a Test PCB: FR4</small>	$T_A = -40^\circ\text{C}/+100^\circ\text{C}$ 15 min each extreme	1000c	1x26	0	0	0
High Temperature Operating Life HTOL <i>JESD22-A108</i> <small>AEC-Q102 #B1a Test PCB: IMS-AI</small>	$T_A = 85^\circ\text{C}; T_S = 100^\circ\text{C};$ $T_J = 110^\circ\text{C}; I_F = 30 \text{ mA}$	1000h	1x26	0	0	0
Pulsed Operating Life PLT <i>JESD22-A108</i> <small>AEC-Q102 #B3 Test PCB: FR4</small>	$T_A = 25^\circ\text{C}$ $I_F = 120 \text{ mA}; t_p = 0,1 \text{ ms};$ $D = 3\%$	1000h	1x26	0	0	0
Dew DEW <i>AEC-Q102-001</i> <small>AEC-Q102 #C7 Test PCB: FR4</small>	$T_{A,\text{min}} = 10^\circ\text{C}$ $T_{A,\text{max}} = 80^\circ\text{C}$ $\text{r.H.} = 53-100\%$ $I_F = 5 \text{ mA}$	10c	1x26	0	0	0
Solderability SD <i>IEC 60068-2-58</i> <small>AEC-Q102 #C10</small>	$T_A = 235^\circ\text{C}$ method 2 (reflow simulation)	1x	1x10	-	-	0
Hydrogen Sulphide H2S <i>IEC 60068-2-43</i> <small>AEC-Q102 #C12 Test PCB: FR4</small>	15 ppm H <sub>2</sub> S 40°C/90% r.H.	336h	1x26	0	0	0
Flowing Mixed Gas FMG <i>IEC 60068-2-60</i> <small>AEC-Q102 #C13 Test PCB: FR4</small>	$T_A = 25^\circ\text{C},$ $\text{r.H.} = 75\%$ Test method 4	500h	1x26	0	0	0
Board Flex Test BF <i>AEC-Q102-002</i> <small>AEC-Q102 #C14 Test PCB: FR4</small>	2 mm	1x	1x10	0	0	0
Electrostatic Discharge HBM <i>ANSI/ESDA/ JEDEC JS-001</i> <small>AEC-Q102 #E3 Test PCB: FR4</small>	Human Body Model	2000V	1x10	0	0	0



Constant Acceleration CA	<i>MIL-STD-750-2</i> AEC-Q102 #G1	Method 2006 2000 gf; 1 min in x/y/z (+/- direction)	1x	3x10	
Vibration Variable Frequency VVF	<i>JESD22-B103</i> AEC-Q102 #G2	20g, 20-2000Hz; 4min / cy; 4cy/axis service condition 1	1x	sequential samples	for uncasted packages only
Mechanical Shock MS	<i>JESD22-B110</i> AEC-Q102 #G3	1500g for 0.5ms, 5 blows, 3 orientations	1x	sequential samples	
Hermeticity HER	<i>JESD22-A109</i> AEC-Q102 #G4	Leak Test: Fine & Gross	1x	sequential samples	

### Additional Tests to AEC Q102

Test Performed	Condition	Duration	Sample Size	Failures			
				El.	Opt.	Vis	
Electrostatic Discharge MM	<i>JESD22-A115</i> Test PCB: FR4	Machine Model	200V	1x10	0	0	0

### LO T676:

#### Failure criteria:

Electrical failures:	$V_f$ ( $I_f = 20$ mA)	$> 2,35V; \pm 10\%$ from initial value
Optical failures:	$I_v$ ( $I_f = 20$ mA) $\lambda_{dom}$ ( $I_f = 20$ mA)	absolute limit: $\pm 50\%$ max. $\pm 2$ nm from initial value
Visual failures:	acc JEDEC JESD22-B101	

**Conclusion: The tested devices representing the product family as stated in the applies to section fulfill the reliability requirements of AEC-Q102 Rev-A.**

Pre-conditioning according to Jedec Level II where applicable as per AEC-Q102 AEC-Q102 #A1 LP T676 (Chip C)

Test Performed	Condition	Duration	Sample Size	Failures		
				El.	Opt.	Vis
				<small>AEC-Q102 #E1</small>	<small>AEC-Q102 #E1</small>	<small>AEC-Q102 #E0</small>
Wet High Temperature Operating Life WHTOL1 <i>JESD22-A101</i> <small>AEC-Q102 #A2a Test PCB: IMS-AI</small>	$T_A = 85^\circ\text{C}; T_S = 100^\circ\text{C};$ $T_J = 110^\circ\text{C}; \text{r.H.} = 85\%$ $I_F = 30 \text{ mA}$ $T_{\text{on/off}} = 30 \text{ min}$	1000h	1x26	0	0	0
Wet High Temperature Operating Life WHTOL2 <i>JESD22-A101</i> <small>AEC-Q102 #A2b Test PCB: FR4</small>	$T_A = 85^\circ\text{C}; \text{r.H.} = 85\%$ $I_F = 5 \text{ mA}$	1000h	1x26	0	0	0
Powered Temperature Cycle PTC <i>JESD22-A105</i> <small>AEC-Q102 #A3a Test PCB: IMS-AI</small>	$T_A = -40^\circ\text{C}/+85^\circ\text{C}; T_S = 100^\circ\text{C};$ $T_J = 105^\circ\text{C}; I_F = 30 \text{ mA}$ $t_{\text{on/off}} = 5 \text{ min}$	1000c	1x26	0	0	0
Temperature Cycling TC <i>JESD22-A104</i> <small>AEC-Q102 #A4a Test PCB: FR4</small>	$T_A = -40^\circ\text{C}/+100^\circ\text{C}$ 15 min each extreme	1000c	1x26	0	0	0
High Temperature Operating Life HTOL <i>JESD22-A108</i> <small>AEC-Q102 #B1a Test PCB: IMS-AI</small>	$T_A = 85^\circ\text{C}; T_S = 100^\circ\text{C};$ $T_J = 105^\circ\text{C}; I_F = 30 \text{ mA}$	1000h	1x26	0	0	0
Pulsed Operating Life PLT <i>JESD22-A108</i> <small>AEC-Q102 #B3 Test PCB: FR4</small>	$T_A = 25^\circ\text{C}$ $I_F = 50 \text{ mA}; t_p = 0,1 \text{ ms};$ $D = 3\%$	1000h	1x26	0	0	0
Dew DEW <i>AEC-Q102-001</i> <small>AEC-Q102 #C7 Test PCB: FR4</small>	$T_{A,\text{min}} = 10^\circ\text{C}$ $T_{A,\text{max}} = 80^\circ\text{C}$ $\text{r.H.} = 53\text{-}100\%$ $I_F = 5 \text{ mA}$	10c	1x26	0	0	0
Solderability SD <i>IEC 60068-2-58</i> <small>AEC-Q102 #C10</small>	$T_A = 235^\circ\text{C}$ method 2 (reflow simulation)	1x	1x10	-	-	0
Hydrogen Sulphide H2S <i>IEC 60068-2-43</i> <small>AEC-Q102 #C12 Test PCB: FR4</small>	15 ppm H <sub>2</sub> S 40°C/90% r.H.	336h	1x26	0	0	0
Flowing Mixed Gas FMG <i>IEC 60068-2-60</i> <small>AEC-Q102 #C13 Test PCB: FR4</small>	$T_A = 25^\circ\text{C},$ $\text{r.H.} = 75\%$ Test method 4	500h	1x26	0	0	0
Board Flex Test BF <i>AEC-Q102-002</i> <small>AEC-Q102 #C14 Test PCB: FR4</small>	2 mm	1x	1x10	0	0	0
Electrostatic Discharge HBM <i>ANSI/ESDA/ JEDEC JS-001</i> <small>AEC-Q102 #E3 Test PCB: FR4</small>	Human Body Model	2000V	1x10	0	0	0

Constant Acceleration CA	<i>MIL-STD-750-2</i> AEC-Q102 #G1	Method 2006 2000 gf; 1 min in x/y/z (+/- direction)	1x	1x10	
Vibration Variable Frequency VVF	<i>JESD22-B103</i> AEC-Q102 #G2	20g, 20-2000Hz; 4min / cy; 4cy/axis service condition 1	1x	sequential samples	for uncasted packages only
Mechanical Shock MS	<i>JESD22-B110</i> AEC-Q102 #G3	1500g for 0.5ms, 5 blows, 3 orientations	1x	sequential samples	
Hermeticity HER	<i>JESD22-A109</i> AEC-Q102 #G4	Leak Test: Fine & Gross	1x	sequential samples	

### Additional Tests to AEC Q102

Test Performed	Condition	Duration	Sample Size	Failures			
				El.	Opt.	Vis	
Electrostatic Discharge MM	<i>JESD22-A115</i> Test PCB: FR4	Machine Model	200V	1x10	0	0	0

### LP T676:

#### Failure criteria:

Electrical failures:	$V_f$ ( $I_f = 20$ mA)	$> 2,4V; \pm 10\%$ from initial value
Optical failures:	$I_v$ ( $I_f = 20$ mA) $\lambda_{dom}$ ( $I_f = 20$ mA)	absolute limit: $\pm 50\%$ max. $\pm 2$ nm from initial value
Visual failures:	acc JEDEC JESD22-B101	

**Conclusion: The tested devices representing the product family as stated in the applies to section fulfill the reliability requirements of AEC-Q102 Rev-A.**

Pre-conditioning according to Jedec Level II where applicable as per AEC-Q102 AEC-Q102 #A1 **LS T67K (Chip D)**

Test Performed	Condition	Duration	Sample Size	Failures		
				El.	Opt.	Vis
				<small>AEC-Q102 #E1</small>	<small>AEC-Q102 #E1</small>	<small>AEC-Q102 #E0</small>
Wet High Temperature Operating Life WHTOL1 <i>JESD22-A101</i> <small>AEC-Q102 #A2a Test PCB: IMS-AI</small>	$T_A = 85^\circ\text{C}; T_S = 95^\circ\text{C};$ $T_J = 105^\circ\text{C}; \text{r.H.} = 85\%$ $I_F = 20 \text{ mA}$ $T_{\text{on/off}} = 30 \text{ min}$	1000h	1x26	0	0	0
Wet High Temperature Operating Life WHTOL2 <i>JESD22-A101</i> <small>AEC-Q102 #A2b Test PCB: FR4</small>	$T_A = 85^\circ\text{C}; \text{r.H.} = 85\%$ $I_F = 5 \text{ mA}$	1000h	1x26	0	0	0
Powered Temperature Cycle PTC <i>JESD22-A105</i> <small>AEC-Q102 #A3a Test PCB: IMS-AI</small>	$T_A = -40^\circ\text{C}/+100^\circ\text{C}; T_S = 100^\circ\text{C};$ $T_J = 105^\circ\text{C}; I_F = 5 \text{ mA}$ $t_{\text{on/off}} = 5 \text{ min}$	1000c	1x26	0	0	0
Temperature Cycling TC <i>JESD22-A104</i> <small>AEC-Q102 #A4a Test PCB: FR4</small>	$T_A = -40^\circ\text{C}/+100^\circ\text{C}$ 15 min each extreme	1000c	1x26	0	0	0
High Temperature Operating Life HTOL <i>JESD22-A108</i> <small>AEC-Q102 #B1a Test PCB: IMS-AI</small>	$T_A = 85^\circ\text{C}; T_S = 95^\circ\text{C};$ $T_J = 105^\circ\text{C}; I_F = 20 \text{ mA}$	1000h	1x26	0	0	0
Pulsed Operating Life PLT <i>JESD22-A108</i> <small>AEC-Q102 #B3 Test PCB: FR4</small>	$T_A = 25^\circ\text{C}$ $I_F = 100 \text{ mA}; t_p = 0,1 \text{ ms};$ $D = 3\%$	1000h	1x26	0	0	0
Dew DEW <i>AEC-Q102-001</i> <small>AEC-Q102 #C7 Test PCB: FR4</small>	$T_{A,\text{min}} = 10^\circ\text{C}$ $T_{A,\text{max}} = 80^\circ\text{C}$ $\text{r.H.} = 53\text{-}100\%$ $I_F = 5 \text{ mA}$	10c	1x26	0	0	0
Solderability SD <i>IEC 60068-2-58</i> <small>AEC-Q102 #C10</small>	$T_A = 235^\circ\text{C}$ method 2 (reflow simulation)	1x	1x10	-	-	0
Hydrogen Sulphide H2S <i>IEC 60068-2-43</i> <small>AEC-Q102 #C12 Test PCB: FR4</small>	15 ppm H <sub>2</sub> S 40°C/90% r.H.	336h	1x26	0	0	0
Flowing Mixed Gas FMG <i>IEC 60068-2-60</i> <small>AEC-Q102 #C13 Test PCB: FR4</small>	$T_A = 25^\circ\text{C},$ $\text{r.H.} = 75\%$ Test method 4	500h	1x26	0	0	0
Board Flex Test BF <i>AEC-Q102-002</i> <small>AEC-Q102 #C14 Test PCB: FR4</small>	2 mm	1x	1x10	0	0	0
Electrostatic Discharge HBM <i>ANSI/ESDA/ JEDEC JS-001</i> <small>AEC-Q102 #E3 Test PCB: FR4</small>	Human Body Model	2000V	1x10	0	0	0

Constant Acceleration CA	<i>MIL-STD-750-2</i> AEC-Q102 #G1	Method 2006 2000 gf; 1 min in x/y/z (+/- direction)	1x	2x10	
Vibration Variable Frequency VVF	<i>JESD22-B103</i> AEC-Q102 #G2	20g, 20-2000Hz; 4min / cy; 4cy/axis service condition 1	1x	sequential samples	for uncasted packages only
Mechanical Shock MS	<i>JESD22-B110</i> AEC-Q102 #G3	1500g for 0.5ms, 5 blows, 3 orientations	1x	sequential samples	
Hermeticity HER	<i>JESD22-A109</i> AEC-Q102 #G4	Leak Test: Fine & Gross	1x	sequential samples	

### Additional Tests to AEC Q102

Test Performed	Condition	Duration	Sample Size	Failures			
				El.	Opt.	Vis	
Electrostatic Discharge MM	<i>JESD22-A115</i> Test PCB: FR4	Machine Model	200V	1x10	0	0	0

### LS T67K:

#### Failure criteria:

Electrical failures:	$V_f (I_f = 2 \text{ mA})$	$> 2,20\text{V}; \pm 10\%$ from initial value
Optical failures:	$I_v (I_f = 2 \text{ mA})$ $\lambda_{\text{dom}} (I_f = 2 \text{ mA})$	absolute limit: $\pm 50\%$ max. $\pm 2 \text{ nm}$ from initial value
Visual failures:	acc JEDEC JESD22-B101	

**Conclusion: The tested devices representing the product family as stated in the applies to section fulfill the reliability requirements of AEC-Q102 Rev-A.**

## Pre-conditioning according to Jedec Level II where applicable as per AEC-Q102 AEC-Q102 #A1 LY T67K (Chip D)

Test Performed	Condition	Duration	Sample Size	Failures		
				EI. <small>AEC-Q102 #E1</small>	Opt. <small>AEC-Q102 #E1</small>	Vis <small>AEC-Q102 #E0</small>
Wet High Temperature Operating Life WHTOL1 <i>JESD22-A101</i> <small>AEC-Q102 #A2a Test PCB: IMS-AI</small>	$T_A = 85^\circ\text{C}; T_S = 95^\circ\text{C};$ $T_J = 105^\circ\text{C}; \text{r.H.} = 85\%$ $I_F = 20 \text{ mA}$ $T_{\text{on/off}} = 30 \text{ min}$	1000h	2x26	0	0	0
Wet High Temperature Operating Life WHTOL2 <i>JESD22-A101</i> <small>AEC-Q102 #A2b Test PCB: FR4</small>	$T_A = 85^\circ\text{C}; \text{r.H.} = 85\%$ $I_F = 5 \text{ mA}$	1000h	2x26	0	0	0
Powered Temperature Cycle PTC <i>JESD22-A105</i> <small>AEC-Q102 #A3a Test PCB: IMS-AI</small>	$T_A = -40^\circ\text{C}/+100^\circ\text{C}; T_S = 95^\circ\text{C};$ $T_J = 105^\circ\text{C}; I_F = 5 \text{ mA}$ $t_{\text{on/off}} = 5 \text{ min}$	1000c	2x26	0	0	0
Temperature Cycling TC <i>JESD22-A104</i> <small>AEC-Q102 #A4a Test PCB: FR4</small>	$T_A = -40^\circ\text{C}/+100^\circ\text{C}$ 15 min each extreme	1000c	2x26	0	0	0
High Temperature Operating Life HTOL <i>JESD22-A108</i> <small>AEC-Q102 #B1a Test PCB: IMS-AI</small>	$T_A = 85^\circ\text{C}; T_S = 100^\circ\text{C};$ $T_J = 105^\circ\text{C}; I_F = 20 \text{ mA}$	1000h	2x26	0	0	0
Pulsed Operating Life PLT <i>JESD22-A108</i> <small>AEC-Q102 #B3 Test PCB: FR4</small>	$T_A = 25^\circ\text{C}$ $I_F = 100 \text{ mA}; t_p = 0,1 \text{ ms};$ $D = 3\%$	1000h	1x26	0	0	0
Dew DEW <i>AEC-Q102-001</i> <small>AEC-Q102 #C7 Test PCB: FR4</small>	$T_{A,\text{min}} = 10^\circ\text{C}$ $T_{A,\text{max}} = 80^\circ\text{C}$ $\text{r.H.} = 53-100\%$ $I_F = 5 \text{ mA}$	10c	2x26	0	0	0
Solderability SD <i>IEC 60068-2-58</i> <small>AEC-Q102 #C10</small>	$T_A = 235^\circ\text{C}$ method 2 (reflow simulation)	1x	2x10	-	-	0
Hydrogen Sulphide H2S <i>IEC 60068-2-43</i> <small>AEC-Q102 #C12 Test PCB: FR4</small>	15 ppm H <sub>2</sub> S 40°C/90% r.H.	336h	2x26	0	0	0
Flowing Mixed Gas FMG <i>IEC 60068-2-60</i> <small>AEC-Q102 #C13 Test PCB: FR4</small>	$T_A = 25^\circ\text{C},$ $\text{r.H.} = 75\%$ Test method 4	500h	2x26	0	0	0
Board Flex Test BF <i>AEC-Q102-002</i> <small>AEC-Q102 #C14 Test PCB: FR4</small>	2 mm	1x	2x10	0	0	0
Electrostatic Discharge HBM <i>ANSI/ESDA/ JEDEC JS-001</i> <small>AEC-Q102 #E3 Test PCB: FR4</small>	Human Body Model	2000V	2x10	0	0	0

Constant Acceleration CA	<i>MIL-STD-750-2</i> AEC-Q102 #G1	Method 2006 2000 gf; 1 min in x/y/z (+/- direction)	1x	2x10	
Vibration Variable Frequency VVF	<i>JESD22-B103</i> AEC-Q102 #G2	20g, 20-2000Hz; 4min / cy; 4cy/axis service condition 1	1x	sequential samples	for uncasted packages only
Mechanical Shock MS	<i>JESD22-B110</i> AEC-Q102 #G3	1500g for 0.5ms, 5 blows, 3 orientations	1x	sequential samples	
Hermeticity HER	<i>JESD22-A109</i> AEC-Q102 #G4	Leak Test: Fine & Gross	1x	sequential samples	

### Additional Tests to AEC Q102

Test Performed	Condition	Duration	Sample Size	Failures			
				El.	Opt.	Vis	
Electrostatic Discharge MM	<i>JESD22-A115</i> Test PCB: FR4	Machine Model	200V	1x10	0	0	0

### LY T67K:

#### Failure criteria:

Electrical failures:  $V_f$  ( $I_f = 2$  mA) > 2,20V;  $\pm 10\%$  from initial value

Optical failures:  $I_v$  ( $I_f = 2$  mA) absolute limit:  $\pm 50\%$  max.  
 $\lambda_{dom}$  ( $I_f = 2$  mA)  $\pm 2$  nm from initial value

Visual failures: acc JEDEC JESD22-B101

**Conclusion: The tested devices representing the product family as stated in the applies to section fulfill the reliability requirements of AEC-Q102 Rev-A.**

Pre-conditioning according to Jedec Level II where applicable as per AEC-Q102 AEC-Q102 #A1 **LG T67K (Chip D)**

Test Performed	Condition	Duration	Sample Size	Failures		
				El.	Opt.	Vis
				<small>AEC-Q102 #E1</small>	<small>AEC-Q102 #E1</small>	<small>AEC-Q102 #E0</small>
Wet High Temperature Operating Life WHTOL1 <i>JESD22-A101</i> <small>AEC-Q102 #A2a Test PCB: IMS-AI</small>	$T_A = 85^\circ\text{C}; T_S = 90^\circ\text{C};$ $T_J = 95^\circ\text{C}; \text{r.H.} = 85\%$ $I_F = 20 \text{ mA}$ $T_{\text{on/off}} = 30 \text{ min}$	1000h	1x26	0	0	0
Wet High Temperature Operating Life WHTOL2 <i>JESD22-A101</i> <small>AEC-Q102 #A2b Test PCB: FR4</small>	$T_A = 85^\circ\text{C}; \text{r.H.} = 85\%$ $I_F = 5 \text{ mA}$	1000h	1x26	0	0	0
Powered Temperature Cycle PTC <i>JESD22-A105</i> <small>AEC-Q102 #A3a Test PCB: IMS-AI</small>	$T_A = -40^\circ\text{C}/+100^\circ\text{C}; T_S = 90^\circ\text{C};$ $T_J = 95^\circ\text{C}; I_F = 5 \text{ mA}$ $t_{\text{on/off}} = 5 \text{ min}$	1000c	1x26	0	0	0
Temperature Cycling TC <i>JESD22-A104</i> <small>AEC-Q102 #A4a Test PCB: FR4</small>	$T_A = -40^\circ\text{C}/+100^\circ\text{C}$ 15 min each extreme	1000c	1x26	0	0	0
High Temperature Operating Life HTOL <i>JESD22-A108</i> <small>AEC-Q102 #B1a Test PCB: IMS-AI</small>	$T_A = 85^\circ\text{C}; T_S = 90^\circ\text{C};$ $T_J = 95^\circ\text{C}; I_F = 20 \text{ mA}$	1000h	1x26	0	0	0
Pulsed Operating Life PLT <i>JESD22-A108</i> <small>AEC-Q102 #B3 Test PCB: FR4</small>	$T_A = 25^\circ\text{C}$ $I_F = 100 \text{ mA}; t_p = 0,1 \text{ ms};$ $D = 3\%$	1000h	1x26	0	0	0
Dew DEW <i>AEC-Q102-001</i> <small>AEC-Q102 #C7 Test PCB: FR4</small>	$T_{A,\text{min}} = 10^\circ\text{C}$ $T_{A,\text{max}} = 80^\circ\text{C}$ $\text{r.H.} = 53\text{-}100\%$ $I_F = 5 \text{ mA}$	10c	1x26	0	0	0
Solderability SD <i>IEC 60068-2-58</i> <small>AEC-Q102 #C10</small>	$T_A = 235^\circ\text{C}$ method 2 (reflow simulation)	1x	1x10	-	-	0
Hydrogen Sulphide H2S <i>IEC 60068-2-43</i> <small>AEC-Q102 #C12 Test PCB: FR4</small>	15 ppm H <sub>2</sub> S 40°C/90% r.H.	336h	1x26	0	0	0
Flowing Mixed Gas FMG <i>IEC 60068-2-60</i> <small>AEC-Q102 #C13 Test PCB: FR4</small>	$T_A = 25^\circ\text{C},$ $\text{r.H.} = 75\%$ Test method 4	500h	1x26	0	0	0
Board Flex Test BF <i>AEC-Q102-002</i> <small>AEC-Q102 #C14 Test PCB: FR4</small>	2 mm	1x	1x10	0	0	0
Electrostatic Discharge HBM <i>ANSI/ESDA/ JEDEC JS-001</i> <small>AEC-Q102 #E3 Test PCB: FR4</small>	Human Body Model	2000V	1x10	0	0	0



Constant Acceleration CA	<i>MIL-STD-750-2</i> AEC-Q102 #G1	Method 2006 2000 gf; 1 min in x/y/z (+/- direction)	1x	1x10	
Vibration Variable Frequency VVF	<i>JESD22-B103</i> AEC-Q102 #G2	20g, 20-2000Hz; 4min / cy; 4cy/axis service condition 1	1x	sequential samples	for uncasted packages only
Mechanical Shock MS	<i>JESD22-B110</i> AEC-Q102 #G3	1500g for 0.5ms, 5 blows, 3 orientations	1x	sequential samples	
Hermeticity HER	<i>JESD22-A109</i> AEC-Q102 #G4	Leak Test: Fine & Gross	1x	sequential samples	

### Additional Tests to AEC Q102

Test Performed	Condition	Duration	Sample Size	Failures			
				El.	Opt.	Vis	
Electrostatic Discharge MM	<i>JESD22-A115</i> Test PCB: FR4	Machine Model	200V	1x10	0	0	0

### LG T67K:

#### Failure criteria:

Electrical failures:  $V_f$  ( $I_f = 2$  mA) > 2,20V;  $\pm 10\%$  from initial value

Optical failures:  $I_v$  ( $I_f = 2$  mA) absolute limit:  $\pm 50\%$  max.  
 $\lambda_{dom}$  ( $I_f = 2$  mA)  $\pm 2$  nm from initial value

Visual failures: acc JEDEC JESD22-B101

**Conclusion: The tested devices representing the product family as stated in the applies to section fulfill the reliability requirements of AEC-Q102 Rev-A.**

## Pre-conditioning according to Jedec Level II where applicable as per AEC-Q102 AEC-Q102 #A1 LS T67K (Chip E)

Test Performed	Condition	Duration	Sample Size	Failures		
				El.	Opt.	Vis
				AEC-Q102 #E1	AEC-Q102 #E1	AEC-Q102 #E0
Wet High Temperature Operating Life WHTOL1 <i>JESD22-A101</i> AEC-Q102 #A2a Test PCB: IMS-AI	$T_A = 85^\circ\text{C}; T_S = 95^\circ\text{C};$ $T_J = 105^\circ\text{C}; \text{r.H.} = 85\%$ $I_F = 20 \text{ mA}$ $T_{\text{on/off}} = 30 \text{ min}$	1000h	1x26	0	0	0
Wet High Temperature Operating Life WHTOL2 <i>JESD22-A101</i> AEC-Q102 #A2b Test PCB: FR4	$T_A = 85^\circ\text{C}; \text{r.H.} = 85\%$ $I_F = 5 \text{ mA}$	1000h	1x26	0	0	0
Powered Temperature Cycle PTC <i>JESD22-A105</i> AEC-Q102 #A3a Test PCB: IMS-AI	$T_A = -40^\circ\text{C}/+100^\circ\text{C}; T_S = 100^\circ\text{C};$ $T_J = 105^\circ\text{C}; I_F = 5 \text{ mA}$ $t_{\text{on/off}} = 5 \text{ min}$	1000c	1x26	0	0	0
Temperature Cycling TC <i>JESD22-A104</i> AEC-Q102 #A4a Test PCB: FR4	$T_A = -40^\circ\text{C}/+100^\circ\text{C}$ 15 min each extreme	1000c	1x26	0	0	0
High Temperature Operating Life HTOL <i>JESD22-A108</i> AEC-Q102 #B1a Test PCB: IMS-AI	$T_A = 85^\circ\text{C}; T_S = 95^\circ\text{C};$ $T_J = 105^\circ\text{C}; I_F = 20 \text{ mA}$	1000h	1x26	0	0	0
Pulsed Operating Life PLT <i>JESD22-A108</i> AEC-Q102 #B3 Test PCB: FR4	$T_A = 25^\circ\text{C}$ $I_F = 100 \text{ mA}; t_p = 0,1 \text{ ms};$ $D = 3\%$	1000h	1x26	0	0	0
Dew DEW <i>AEC-Q102-001</i> AEC-Q102 #C7 Test PCB: FR4	$T_{A,\text{min}} = 10^\circ\text{C}$ $T_{A,\text{max}} = 80^\circ\text{C}$ $\text{r.H.} = 53\text{-}100\%$ $I_F = 5 \text{ mA}$	10c	1x26	0	0	0
Solderability SD <i>IEC 60068-2-58</i> AEC-Q102 #C10	$T_A = 235^\circ\text{C}$ method 2 (reflow simulation)	1x	1x10	-	-	0
Hydrogen Sulphide H2S <i>IEC 60068-2-43</i> AEC-Q102 #C12 Test PCB: FR4	15 ppm H <sub>2</sub> S 40°C/90% r.H.	336h	1x26	0	0	0
Flowing Mixed Gas FMG <i>IEC 60068-2-60</i> AEC-Q102 #C13 Test PCB: FR4	$T_A = 25^\circ\text{C},$ $\text{r.H.} = 75\%$ Test method 4	500h	1x26	0	0	0
Board Flex Test BF <i>AEC-Q102-002</i> AEC-Q102 #C14 Test PCB: FR4	2 mm	1x	1x10	0	0	0
Electrostatic Discharge HBM <i>ANSI/ESDA/ JEDEC JS-001</i> AEC-Q102 #E3 Test PCB: FR4	Human Body Model	2000V	1x10	0	0	0

Constant Acceleration CA	<i>MIL-STD-750-2</i> AEC-Q102 #G1	Method 2006 2000 gf; 1 min in x/y/z (+/- direction)	1x	1x10	
Vibration Variable Frequency VVF	<i>JESD22-B103</i> AEC-Q102 #G2	20g, 20-2000Hz; 4min / cy; 4cy/axis service condition 1	1x	sequential samples	for uncasted packages only
Mechanical Shock MS	<i>JESD22-B110</i> AEC-Q102 #G3	1500g for 0.5ms, 5 blows, 3 orientations	1x	sequential samples	
Hermeticity HER	<i>JESD22-A109</i> AEC-Q102 #G4	Leak Test: Fine & Gross	1x	sequential samples	

### Additional Tests to AEC Q102

Test Performed	Condition	Duration	Sample Size	Failures			
				El.	Opt.	Vis	
Electrostatic Discharge MM	<i>JESD22-A115</i> Test PCB: FR4	Machine Model	200V	1x10	0	0	0

### LS T67K:

#### Failure criteria:

Electrical failures:  $V_f$  ( $I_f = 2$  mA) > 2,20V;  $\pm 10\%$  from initial value

Optical failures:  $I_v$  ( $I_f = 2$  mA) absolute limit:  $\pm 50\%$  max.  
 $\lambda_{dom}$  ( $I_f = 2$  mA)  $\pm 2$  nm from initial value

Visual failures: acc JEDEC JESD22-B101

**Conclusion: The tested devices representing the product family as stated in the applies to section fulfill the reliability requirements of AEC-Q102 Rev-A.**

Pre-conditioning according to Jedec Level II where applicable as per AEC-Q102 AEC-Q102 #A1 LY T67K (Chip E)

Test Performed	Condition	Duration	Sample Size	Failures		
				El.	Opt.	Vis
				<small>AEC-Q102 #E1</small>	<small>AEC-Q102 #E1</small>	<small>AEC-Q102 #E0</small>
Wet High Temperature Operating Life WHTOL1 <i>JESD22-A101</i> <small>AEC-Q102 #A2a Test PCB: IMS-AI</small>	$T_A = 85^\circ\text{C}; T_S = 95^\circ\text{C};$ $T_J = 105^\circ\text{C}; \text{r.H.} = 85\%$ $I_F = 20 \text{ mA}$ $T_{\text{on/off}} = 30 \text{ min}$	1000h	1x26	0	0	0
Wet High Temperature Operating Life WHTOL2 <i>JESD22-A101</i> <small>AEC-Q102 #A2b Test PCB: FR4</small>	$T_A = 85^\circ\text{C}; \text{r.H.} = 85\%$ $I_F = 5 \text{ mA}$	1000h	1x26	0	0	0
Powered Temperature Cycle PTC <i>JESD22-A105</i> <small>AEC-Q102 #A3a Test PCB: IMS-AI</small>	$T_A = -40^\circ\text{C}/+100^\circ\text{C}; T_S = 100^\circ\text{C};$ $T_J = 105^\circ\text{C}; I_F = 5 \text{ mA}$ $t_{\text{on/off}} = 5 \text{ min}$	1000c	1x26	0	0	0
Temperature Cycling TC <i>JESD22-A104</i> <small>AEC-Q102 #A4a Test PCB: FR4</small>	$T_A = -40^\circ\text{C}/+100^\circ\text{C}$ 15 min each extreme	1000c	1x26	0	0	0
High Temperature Operating Life HTOL <i>JESD22-A108</i> <small>AEC-Q102 #B1a Test PCB: IMS-AI</small>	$T_A = 85^\circ\text{C}; T_S = 95^\circ\text{C};$ $T_J = 105^\circ\text{C}; I_F = 20 \text{ mA}$	1000h	1x26	0	0	0
Pulsed Operating Life PLT <i>JESD22-A108</i> <small>AEC-Q102 #B3 Test PCB: FR4</small>	$T_A = 25^\circ\text{C}$ $I_F = 100 \text{ mA}; t_p = 0,1 \text{ ms};$ $D = 3\%$	1000h	1x26	0	0	0
Dew DEW <i>AEC-Q102-001</i> <small>AEC-Q102 #C7 Test PCB: FR4</small>	$T_{A,\text{min}} = 10^\circ\text{C}$ $T_{A,\text{max}} = 80^\circ\text{C}$ $\text{r.H.} = 53\text{-}100\%$ $I_F = 5 \text{ mA}$	10c	1x26	0	0	0
Solderability SD <i>IEC 60068-2-58</i> <small>AEC-Q102 #C10</small>	$T_A = 235^\circ\text{C}$ method 2 (reflow simulation)	1x	1x10	-	-	0
Hydrogen Sulphide H2S <i>IEC 60068-2-43</i> <small>AEC-Q102 #C12 Test PCB: FR4</small>	15 ppm H <sub>2</sub> S 40°C/90% r.H.	336h	1x26	0	0	0
Flowing Mixed Gas FMG <i>IEC 60068-2-60</i> <small>AEC-Q102 #C13 Test PCB: FR4</small>	$T_A = 25^\circ\text{C},$ $\text{r.H.} = 75\%$ Test method 4	500h	1x26	0	0	0
Board Flex Test BF <i>AEC-Q102-002</i> <small>AEC-Q102 #C14 Test PCB: FR4</small>	2 mm	1x	1x10	0	0	0
Electrostatic Discharge HBM <i>ANSI/ESDA/ JEDEC JS-001</i> <small>AEC-Q102 #E3 Test PCB: FR4</small>	Human Body Model	2000V	1x10	0	0	0

Constant Acceleration CA	<i>MIL-STD-750-2</i> AEC-Q102 #G1	Method 2006 2000 gf; 1 min in x/y/z (+/- direction)	1x	1x10	
Vibration Variable Frequency VVF	<i>JESD22-B103</i> AEC-Q102 #G2	20g, 20-2000Hz; 4min / cy; 4cy/axis service condition 1	1x	sequential samples	for uncasted packages only
Mechanical Shock MS	<i>JESD22-B110</i> AEC-Q102 #G3	1500g for 0.5ms, 5 blows, 3 orientations	1x	sequential samples	
Hermeticity HER	<i>JESD22-A109</i> AEC-Q102 #G4	Leak Test: Fine & Gross	1x	sequential samples	

### Additional Tests to AEC Q102

Test Performed	Condition	Duration	Sample Size	Failures		
				El.	Opt.	Vis
Electrostatic Discharge MM	<i>JESD22-A115</i> Machine Model Test PCB: FR4	200V	1x10	0	0	0

### LY T67K:

#### Failure criteria:

Electrical failures:  $V_f$  ( $I_f = 2$  mA) > 2,20V;  $\pm 10\%$  from initial value

Optical failures:  $I_v$  ( $I_f = 2$  mA) absolute limit:  $\pm 50\%$  max.  
 $\lambda_{dom}$  ( $I_f = 2$  mA)  $\pm 2$  nm from initial value

Visual failures: acc JEDEC JESD22-B101

**Conclusion: The tested devices representing the product family as stated in the applies to section fulfill the reliability requirements of AEC-Q102 Rev-A.**

Pre-conditioning according to Jedec Level II where applicable as per AEC-Q102 AEC-Q102 #A1 **LG T67K (Chip E)**

Test Performed	Condition	Duration	Sample Size	Failures		
				El.	Opt.	Vis
				<small>AEC-Q102 #E1</small>	<small>AEC-Q102 #E1</small>	<small>AEC-Q102 #E0</small>
Wet High Temperature Operating Life WHTOL1 <i>JESD22-A101</i> <small>AEC-Q102 #A2a Test PCB: IMS-AI</small>	$T_A = 85^\circ\text{C}; T_S = 95^\circ\text{C};$ $T_J = 105^\circ\text{C}; \text{r.H.} = 85\%$ $I_F = 20 \text{ mA}$ $T_{\text{on/off}} = 30 \text{ min}$	1000h	1x26	0	0	0
Wet High Temperature Operating Life WHTOL2 <i>JESD22-A101</i> <small>AEC-Q102 #A2b Test PCB: FR4</small>	$T_A = 85^\circ\text{C}; \text{r.H.} = 85\%$ $I_F = 5 \text{ mA}$	1000h	1x26	0	0	0
Powered Temperature Cycle PTC <i>JESD22-A105</i> <small>AEC-Q102 #A3a Test PCB: IMS-AI</small>	$T_A = -40^\circ\text{C}/+100^\circ\text{C}; T_S = 100;$ $T_J = 105^\circ\text{C}; I_F = 5 \text{ mA}$ $t_{\text{on/off}} = 5 \text{ min}$	1000c	1x26	0	0	0
Temperature Cycling TC <i>JESD22-A104</i> <small>AEC-Q102 #A4a Test PCB: FR4</small>	$T_A = -40^\circ\text{C}/+100^\circ\text{C}$ 15 min each extreme	1000c	1x26	0	0	0
High Temperature Operating Life HTOL <i>JESD22-A108</i> <small>AEC-Q102 #B1a Test PCB: IMS-AI</small>	$T_A = 85^\circ\text{C}; T_S = 95^\circ\text{C};$ $T_J = 105^\circ\text{C}; I_F = 20 \text{ mA}$	1000h	1x26	0	0	0
Pulsed Operating Life PLT <i>JESD22-A108</i> <small>AEC-Q102 #B3 Test PCB: FR4</small>	$T_A = 25^\circ\text{C}$ $I_F = 100 \text{ mA}; t_p = 0,1 \text{ ms};$ $D = 3\%$	1000h	1x26	0	0	0
Dew DEW <i>AEC-Q102-001</i> <small>AEC-Q102 #C7 Test PCB: FR4</small>	$T_{A,\text{min}} = 10^\circ\text{C}$ $T_{A,\text{max}} = 80^\circ\text{C}$ $\text{r.H.} = 53\text{-}100\%$ $I_F = 5 \text{ mA}$	10c	1x26	0	0	0
Solderability SD <i>IEC 60068-2-58</i> <small>AEC-Q102 #C10</small>	$T_A = 235^\circ\text{C}$ method 2 (reflow simulation)	1x	1x10	-	-	0
Hydrogen Sulphide H2S <i>IEC 60068-2-43</i> <small>AEC-Q102 #C12 Test PCB: FR4</small>	15 ppm H <sub>2</sub> S 40°C/90% r.H.	336h	1x26	0	0	0
Flowing Mixed Gas FMG <i>IEC 60068-2-60</i> <small>AEC-Q102 #C13 Test PCB: FR4</small>	$T_A = 25^\circ\text{C},$ $\text{r.H.} = 75\%$ Test method 4	500h	1x26	0	0	0
Board Flex Test BF <i>AEC-Q102-002</i> <small>AEC-Q102 #C14 Test PCB: FR4</small>	2 mm	1x	1x10	0	0	0
Electrostatic Discharge HBM <i>ANSI/ESDA/ JEDEC JS-001</i> <small>AEC-Q102 #E3 Test PCB: FR4</small>	Human Body Model	2000V	1x10	0	0	0

Constant Acceleration CA	<i>MIL-STD-750-2</i> AEC-Q102 #G1	Method 2006 2000 gf; 1 min in x/y/z (+/- direction)	1x	1x10	
Vibration Variable Frequency VVF	<i>JESD22-B103</i> AEC-Q102 #G2	20g, 20-2000Hz; 4min / cy; 4cy/axis service condition 1	1x	sequential samples	for uncasted packages only
Mechanical Shock MS	<i>JESD22-B110</i> AEC-Q102 #G3	1500g for 0.5ms, 5 blows, 3 orientations	1x	sequential samples	
Hermeticity HER	<i>JESD22-A109</i> AEC-Q102 #G4	Leak Test: Fine & Gross	1x	sequential samples	

### Additional Tests to AEC Q102

Test Performed	Condition	Duration	Sample Size	Failures		
				El.	Opt.	Vis
Electrostatic Discharge MM	<i>JESD22-A115</i> Machine Model Test PCB: FR4	200V	1x10	0	0	0

### LG T67K:

#### Failure criteria:

Electrical failures:  $V_f$  ( $I_f = 2 \text{ mA}$ ) > 2,20V;  $\pm 10\%$  from initial value

Optical failures:  $I_v$  ( $I_f = 2 \text{ mA}$ ) absolute limit:  $\pm 50\%$  max.  
 $\lambda_{\text{dom}}$  ( $I_f = 2 \text{ mA}$ )  $\pm 2 \text{ nm}$  from initial value

Visual failures: acc JEDEC JESD22-B101

**Conclusion: The tested devices representing the product family as stated in the applies to section fulfill the reliability requirements of AEC-Q102 Rev-A.**

Pre-conditioning according to Jedec Level II where applicable as per AEC-Q102 AEC-Q102 #A1 LP T675 (Chip F)

Test Performed	Condition	Duration	Sample Size	Failures			
				El.	Opt.	Vis	
				<small>AEC-Q102 #E1</small>	<small>AEC-Q102 #E1</small>	<small>AEC-Q102 #E0</small>	
Wet High Temperature Operating Life WHTOL1	<i>JESD22-A101</i> <small>AEC-Q102 #A2a</small> Test PCB: IMS-AI	$T_A = 85^\circ\text{C}; T_S = 100^\circ\text{C};$ $T_J = 105^\circ\text{C}; \text{r.H.} = 85\%$ $I_F = 30 \text{ mA}$ $T_{\text{on/off}} = 30 \text{ min}$	1000h	3x26	0	0	0
Wet High Temperature Operating Life WHTOL2	<i>JESD22-A101</i> <small>AEC-Q102 #A2b</small> Test PCB: FR4	$T_A = 85^\circ\text{C}; \text{r.H.} = 85\%$ $I_F = 5 \text{ mA}$	1000h	3x26	0	0	0
Powered Temperature Cycle PTC	<i>JESD22-A105</i> <small>AEC-Q102 #A3a</small> Test PCB: IMS-AI	$T_A = -40^\circ\text{C}/+85^\circ\text{C}; T_S = 100^\circ\text{C};$ $T_J = 105^\circ\text{C}; I_F = 30 \text{ mA}$ $t_{\text{on/off}} = 5 \text{ min}$	1000c	3x26	0	0	0
Temperature Cycling TC	<i>JESD22-A104</i> <small>AEC-Q102 #A4a</small> Test PCB: FR4	$T_A = -40^\circ\text{C}/+100^\circ\text{C}$ 15 min each extreme	1000c	3x26	0	0	0
High Temperature Operating Life HTOL	<i>JESD22-A108</i> <small>AEC-Q102 #B1a</small> Test PCB: IMS-AI	$T_A = 85^\circ\text{C}; T_S = 110^\circ\text{C};$ $T_J = 120^\circ\text{C}; I_F = 50 \text{ mA}$	1000h	3x26	0	0	0
Pulsed Operating Life PLT	<i>JESD22-A108</i> <small>AEC-Q102 #B3</small> Test PCB: FR4	$T_A = 25^\circ\text{C}$ $I_F = 50 \text{ mA}; t_p = 0,1\text{ms};$ $D = 3\%$	1000h	3x26	0	0	0
Dew DEW	<i>AEC-Q102-001</i> <small>AEC-Q102 #C7</small> Test PCB: FR4	$T_{A,\text{min}} = 10^\circ\text{C}$ $T_{A,\text{max}} = 80^\circ\text{C}$ $\text{r.H.} = 53\text{-}100\%$ $I_F = 5 \text{ mA}$	10c	3x26	0	0	0
Solderability SD	<i>IEC 60068-2-58</i> <small>AEC-Q102 #C10</small>	$T_A = 235^\circ\text{C}$ method 2 (reflow simulation)	1x	3x10	-	-	0
Hydrogen Sulphide H2S	<i>IEC 60068-2-43</i> <small>AEC-Q102 #C12</small> Test PCB: FR4	15 ppm H <sub>2</sub> S 40°C/90% r.H.	336h	3x26	0	0	0
Flowing Mixed Gas FMG	<i>IEC 60068-2-60</i> <small>AEC-Q102 #C13</small> Test PCB: FR4	$T_A = 25^\circ\text{C},$ $\text{r.H.} = 75\%$ Test method 4	500h	3x26	0	0	0
Board Flex Test BF	<i>AEC-Q102-002</i> <small>AEC-Q102 #C14</small> Test PCB: FR4	2 mm	1x	3x10	0	0	0
Electrostatic Discharge HBM	<i>ANSI/ESDA/ JEDEC JS-001</i> <small>AEC-Q102 #E3</small> Test PCB: FR4	Human Body Model	2000V	3x10	0	0	0



Constant Acceleration CA	<i>MIL-STD-750-2</i> AEC-Q102 #G1	Method 2006 2000 gf; 1 min in x/y/z (+/- direction)	1x	3x10	
Vibration Variable Frequency VVF	<i>JESD22-B103</i> AEC-Q102 #G2	20g, 20-2000Hz; 4min / cy; 4cy/axis service condition 1	1x	sequential samples	for uncasted packages only
Mechanical Shock MS	<i>JESD22-B110</i> AEC-Q102 #G3	1500g for 0.5ms, 5 blows, 3 orientations	1x	sequential samples	
Hermeticity HER	<i>JESD22-A109</i> AEC-Q102 #G4	Leak Test: Fine & Gross	1x	sequential samples	

### Additional Tests to AEC Q102

Test Performed	Condition	Duration	Sample Size	Failures			
				El.	Opt.	Vis	
Electrostatic Discharge MM	<i>JESD22-A115</i> Test PCB: FR4	Machine Model	200V	3x10	0	0	0

### LP T675:

#### Failure criteria:

Electrical failures:  $V_f$  ( $I_f = 30$  mA) > 2,40V;  $\pm 10\%$  from initial value

Optical failures:  $I_v$  ( $I_f = 30$  mA) absolute limit:  $\pm 50\%$  max.  
 $\lambda_{dom}$  ( $I_f = 30$  mA)  $\pm 2$  nm from initial value

Visual failures: acc JEDEC JESD22-B101

**Conclusion: The tested devices representing the product family as stated in the applies to section fulfill the reliability requirements of AEC-Q102 Rev-A.**

## Disclaimer

PLEASE CAREFULLY READ THE BELOW TERMS AND CONDITIONS BEFORE USING THE INFORMATION.  
IF YOU DO NOT AGREE WITH ANY OF THESE TERMS AND CONDITIONS, DO NOT USE THE INFORMATION.

The Information contained in this Document does not constitute an independent warranty. The committed behavior is described in the Product data sheet and/or further, mutually agreed specifications.

Distribution of part or all of the contents of this Document to any 3rd party in any form without the prior permission of ams-OSRAM International GmbH is prohibited except in accordance with applicable mandatory law.

Further explanations:

**Data:** The Data used in this Document consider the reliability test results under the mentioned driving conditions only. For Product information on the maximum operating conditions and the OSRAM standard qualification profile please refer to the Product data sheet or contact your local sales partner.

**Conditions:** The conditions for the generation of the Data are as follows:

1. The Data and curves shown in this Document are based on experiments carried out under laboratory conditions on a random sample size of LED/IRED/Laser/Detector with readouts at discrete readout times (where applicable). Thus, the Data above represent a limited number of production lots only and may differ between different assembly lots over time (including chip or package changes). Thus, the behavior of the LED/IRED/Laser/Detector in the final application may differ from the Data. The behavior of the LED/IRED/Laser/Detector at conditions or readout times deviating from those stated above may not be deduced from the Data.

2. If applicable:

a) Extended driving conditions:

The tested driving conditions exceed the maximum limits stated in the Product data sheet. Therefore, a reduced lifetime or an accelerated degradation is expected. Failure limits noted in the Document refer to the testing condition according to the OSRAM standard Product qualification profile and not to the actual testing condition.

b) Extended testing duration:

The testing duration exceed the OSRAM standard qualification profile of the mentioned Product. Failure limits noted in the Document refer to the testing duration according to the OSRAM standard Product qualification profile and not to the actual testing duration.

c) Exceeding standard qualification conditions – (Product data sheet limits not affected):

The tested driving conditions exceed the OSRAM standard qualification profile of the mentioned Product. Therefore a reduced lifetime or an accelerated degradation is expected. Failure limits noted in the Document refer to the testing condition according to the OSRAM standard Product qualification profile and not to the actual testing condition.

3. For long term operation additional failure modes of the chip or package can occur which are not shown in this Document.  
4. Possible differences in the thermal management of OSRAM and customer's setup may lead to a different aging behavior.

END OF DOCUMENT